

C32: MaxCap-BB-OM4 multimode fibre

Properties of cabled bend insensitive OM4 fibre.

General and application

This fibre is a laser-optimised, bend-insensitive graded-index multimode OM4 fibre suitable for transmission speeds of 10 Gb/s or higher. It has a 50 µm core diameter and a 125 µm cladding diameter. The fibre is optimised for maximum transmission properties at 850 nm; but is also well suited for 1300 nm systems. This fibre is fully compliant to the OM4 specification. The fibre supports 1100 m link length for a 1000BASE-SX system and 550 m for a 1000BASE-LX system as well as 550 m for a properly engineered 10GBASE-SX system. In data centres, this fibre supports 150 m for 40BASE-SR and 100 BASE100-SR systems. The outstanding bending performance of this fibre supports future compact cable management.

Standards

IEC 60793-2-10: type A1a.3	EN 50173-1 category OM4
ISO/IEC 11801 category OM4	TIA/EIA-492 AAAD
ISO/IEC 24764	ANSI/TIA/EIA-568.C
ITU G.651.1	IEEE 802.3
EN 60793-2-10: type A1a.3	

Optical properties

Attribute	Measurement method	Units	Limits
Attenuation limit according to IEC 60793-2-10, 850 nm	IEC 60793-1-40	dB/km	≤ 2.5
Attenuation limit according to IEC 60793-2-10, 1300 nm	IEC 60793-1-40	dB/km	≤ 0.8
Inhomogeneity of OTDR trace for any two 1000 metre fibre lengths	IEC 60793-1-40	dB/km	Max. 0.1
Numerical aperture	IEC 60793-1-43	-	0.200 ± 0.015

Cable attenuation

Maximum attenuation value of cable at 850 nm	IEC 60793-1-40	dB/km	≤ 3.0
Maximum attenuation value of cable at 1300 nm	IEC 60793-1-40	dB/km	≤ 1.0

Attenuation variation vs bending

Fibre bending loss R=7.5 mm 850/1300 nm	IEC 60793-1-40	dB	≤ 0.2 / ≤ 0.5
Fibre bending loss R=15 mm 850/1300 nm	IEC 60793-1-40	dB	≤ 0.1 / ≤ 0.3

Bandwidth

Overfilled (OFL) modal bandwidth at 850 nm	IEC 60793-1-41	MHz • km	≥ 3500
Overfilled (OFL) modal bandwidth at 1300 nm	IEC 60793-1-41	MHz • km	≥ 500
Effective Modal Bandwidth (EMB) at 850 nm	IEC 60793-1-49	MHz • km	≥ 4700

Group index of refraction

Group index of refraction at 850 nm	IEC 60793-1-22	-	1.482
Group index of refraction at 1300 nm	IEC 60793-1-22	-	1.477

C32: MaxCap-BB-OM4 multimode fibre

Geometrical properties

Attribute	Measurement method	Units	Limits
Core diameter	IEC 60793-1-20	µm	50 ± 2
Cladding diameter	IEC 60793-1-20	µm	125.0 ± 1.0
Cladding non-circularity	IEC 60793-1-20	%	≤ 0.7
Core non-circularity	IEC 60793-1-20	%	≤ 5
Core-cladding concentricity error	IEC 60793-1-20	µm	≤ 1
Primary coating diameter - uncoloured	IEC 60793-1-21	µm	242 ± 5
Primary coating diameter - coloured	IEC 60793-1-21	µm	250 ± 15
Primary coating non-circularity	IEC 60793-1-21	%	≤ 5
Primary coating-cladding concentricity error	IEC 60793-1-21	µm	≤ 6

Mechanical properties

Attribute	Measurement method	Units	Limits
Proof stress level	IEC 60793-1-30	GPa	≥ 0.7 (≈ 1 %)
Typical average strip force	IEC 60793-1-32	N	1.7
Strip force (peak)	IEC 60793-1-32	N	1.3 ≤ F _{peak.strip} ≤ 8.9

© PRYSMIAN GROUP 2012, All Rights Reserved

All sizes and values without tolerances are reference values. Specifications are for product as supplied by Prysmian Group: any modification or alteration afterwards of product may give different result.

The information contained within this document must not be copied, reprinted or reproduced in any form, either wholly or in part, without the written consent of Prysmian Group. The information is believed to be correct at the time of issue. Prysmian Group reserves the right to amend this specification without prior notice. This specification is not contractually valid unless specifically authorised by Prysmian Group.